

Werkstoff Nr.	DIN bzw. SEW	DIN-Bezeichnung	EN 10088	ASTM
1.4000	17440	X 6 Cr 13	X6Cr13	403
1.4006	17440	X 12 Cr 13	X12Cr13	410
1.4021	17440	X 20 Cr 13	X20Cr13	420
1.4028	17440	X 30 Cr 13	X30Cr13	420 F
1.4034	17440	X 46 Cr 13	X46Cr13	420
1.4057	17440	X 20 CrNi 17 2	X17CrNi16-2	431
1.4104	17440	X 12 CrMoS 17	X14CrMoS17	430 F
1.4112	SEW 400	X 90 CrMoV 18	X90CrMoV18	440 B
1.4116	17440	X 50 CrMoV 15	X50CrMoV15	
1.4120	SEW 400	X 20 CrMo 13		
1.4122	SEW 400	X 35 CrMo 17	X39CrMo17-2	
1.4301	17440	X 5 CrNi 18 10	X5CrNi18-10	304
1.4303	17440	X 5 CrNi 18 12	X4CrNi18-12	305
1.4305	17440	X 10 CrNiS 18 9	X8CrNiS18-9	303
1.4306	17440	X 2 CrNi 19 11	X2CrNi19-11	304 L
1.4307	17440	X 2 CrNi 18 9	X2CrNi18-9	304 L
1.4313	SEW 400	X 4 CrNi 13 4	X3CrNiMo13-4	S 41500
1.4401	17440	X 5 CrNiMo 17 12 2	X5CrNiMo17-11-2	316
1.4404	17440	X 2 CrNiMo 17 13 2	X2CrNiMo17-12-2	316 L
1.4418	SEW 400	X4 CrNiMo 16 5	X4CrNiMo 16-5-1	
1.4429	17440	X 2 CrNiMoN 17 13	X2CrNiMo17-13-3	316 LN
1.4435	17440	X 2 CrNiMo 18 14 3	X2CrNiMo18-14-3	316 L
1.4436	17440	X 5 CrNiMo 17 13 3	X3CrNiMo17-13-3	316
1.4462	SEW 400	X 2 CrNiMoN 22 5 3	X2CrNiMoN22-5-3	S 31803
1.4539	SEW 400	X 1 NiCrMoCuN 25 20 5	X1NiCrMoCu25-20-5	N 08904
1.4541	17440	X 6 CrNiTi 18 10	X6CrNiTi18-10	321
1.4542	17440	X 5 CrNiCuNb 17 4	X5CrNiCuNb16-4	630
1.4550	17440	X 6 CrNiNb 18 10	X6CrNiNb18-10	347
1.4563	SEW 400	X 1 NiCrMoCuN 31 27 4	X1NiCrMoCu31-27-4	N 08028
1.4565	SEW 400	X 3 CrNiMnMoNbN 23 17 5 3		UNS 34565
1.4571	17440	X 6 CrNiMoTi 17 12 2	X6CrNiMoTi17-12-2	316 Ti
1.4713	SEW 470	X 10 CrAl 7		
1.4762	SEW 470	X 10 CrAl 24		446
1.4828	SEW 470	X 15 CrNiSi 20 12		309
1.4841	SEW 470	X 15 CrNiSi 25 20		314
1.4845	SEW 470	X 12 CrNi 25 21		310 S

Technische Änderungen und Liefermöglichkeiten vorbehalten

© DODEN ARMATUREN KG