

Gruppe	EN-Kuzzeichen	EN-Werkstoff-Nr.	DIN-Kurzzeichen	DIN-Werkstoff-Nr.
<b>Kupfer</b>	CU-OF	CW 008A	OF-Cu	2.0040
	Cu-PHC/Cu-HCP	CW 020A/021A	SE-Cu	2.0070
	CU-DHP	CW 024A	SF-Cu	2.0090
	CU-ETP/FRHC	CW 004A/005A	E-Cu 58	2.0060
<b>niedrig legiertes Kupfer</b>	CuCr 1 Zr	CW 106C	CuCrZr	2.1293
<b>Kupfer-Zink Legierungen</b>	CuZn 5	CW 500L	CuZn 5	2.0220
	CuZn 10	CW 501L	CuZn 10	2.0230
	CuZn 15	CW 502L	CuZn 15	2.0240
	CuZn 20	CW 503L	CuZn 20	2.0250
	CuZn 28	CW 504L	CuZn 28	2.0260
	CuZn 30/33	CW 505/506L	CuZn 30/33	2.0265/2.0280
	CuZn 36	CW 507L	CuZn 36	2.0335
	CuZn 37	CW 508L	CuZn 37	2.0321
	CuZn 40	CW 509L	CuZn 40	2.0360
	CuZn 37 Pb 0,5	CW 604N	CuZn 37 Pb 0,5	2.0332
	CuZn 35 Pb 1	CW 600N	CuZn 36 Pb 1,5	2.0331
	CuZn 38 Pb 1	CW 607N	CuZn 38 Pb 1,5	2.0371
	CuZn 39 Pb 0,5	CW 610N	CuZn 39 Pb 0,5	2.0372
	CuZn 36 Pb 3	CW 603N	CuZn 36 Pb 3	2.0375
	CuZn 39 Pb 2	CW 612N	CuZn 39 Pb 2	2.0380
	CuZn 40 Pb 2	CW 617N	CuZn 40 Pb 2	2.0402
	CuZn 39 Pb 3	CW 614N	CuZn 39 Pb 3	2.0401
	CuZn 36 Pb 2As	CW 602N		
	CuZn 43 Pb 2	CW 623N	CuZn 44 Pb 2	2.0410
	CuZn 28 Sn 1As	CW 706R	CuZn 28 Sn 1	2.0470
	CuZn 31 Si 1	CW 708R	CuZn 31 Si 1	2.0490
	CuZn 35 Ni 3 Mn 2 AlPb	CW 710R	CuZn 35 Ni 2	2.0540
	CuZn 38 Mn 1 Al	CW 716R	CuZn 37 Al 1	2.0510
	CuZn 40 Mn 2 Fe 1	CW 723R	CuZn 40 Mn 2	2.0572
	CuZn 37 Mn 3 Al 2 SiPb	CW 713R	CuZn 40 Al 2	2.0550
	CuZn 20 Al 2 As	CW 720R	CuZn 20 Al 2	2.0460
<b>Kupfer-Zinn Legierungen</b>	CuSn 4	CW 450K	CuSn 4	2.1016
	CuSn 6	CW 452K	CuSn 6	2.1020
	CuSn 8	CW 453K	CuSn 8	2.1030
			CuSn 6 Zn 6	2.1080
<b>Kupfer-Nickel Zinklegierungen</b>	CuNi 12 Zn 24	CW 403J	CuNi 12 Zn 24	2.0730
	CuNi 18 Zn 27	CW 410J	CuNi 18 Zn 27	2.0742
	CuNi 18 Zn 20	CW 409J	CuNi 18 Zn 20	2.0740
			CuNi 7 Zn 39 Mn 5 Pb 3	2.0771
	CuNi 12 Zn 30 Pb 1	CW 406J	CuNi 12 Zn 30 Pb 1	2.0780
CuNi 18 Zn 19 Pb 1	CW 408J	CuNi 18 Zn 19 Pb 1	2.0790	
<b>Kupfer-Nickel Legierungen</b>	CuNi 10 Fe 1 Mn	CW 325H	CuNi 10 Fe 1 Mn	2.0872
	CuNi 30 Mn 1 Fe	CW 354H	CuNi 30 Mn 1 Fe	2.0882
	CuNi 9 Sn 2	CW 351H	CuNi 9 Sn 2	2.0875
<b>Strangguss- Legierungen</b>	CuSn 7 Zn 4 Pb 7-C-GC	CC 493K	GC-CuSn 7 Zn Pb	2.1090
	CuSn 12-C-GC	CC 483K	GC-Cu Sn 12	2.1052
	CuSn 10 Pb 10-C-GC	CC 495K	GC-CuPb 10 Sn	2.1176
	CuSn 7 Pb 15-C-GC	CC 496K	GC-CuPb 15 Sn	2.1182
	CuSn 11 Pb 2-C-GC	CC 482K	GC-CuSn 12 Pb	2.1061
	CuSn 12 Ni 2-C-GC	CC 484K	GC-CuSn 12 Ni	2.1060